

Impurities and Conductivity in a *D*-wave Superconductor*

A. V. Balatsky[†]

Theoretical Division, Los Alamos National Laboratory, Los Alamos, NM 87544

Abstract

Impurity scattering in the unitary limit produces low energy quasiparticles with anisotropic spectrum in a two-dimensional *d*-wave superconductor. We describe a new *quasi-one-dimensional* limit of the quasiparticle scattering, which might occur in a superconductor with short coherence length and with *finite* impurity potential range. The dc conductivity in a *d*-wave superconductor is predicted to be proportional to the normal state scattering rate and is impurity-*dependent*. We show that *quasi-one-dimensional* regime might occur in high- T_c superconductors with Zn impurities at low temperatures $T \lesssim 10$ K.

PACS Nos. 74.25.Fy; 71.55.Jv; 74.20.Mn

Typeset using REVTeX

Paper presented at the Los Alamos Conference on Strongly Correlated Electron Systems, December 1993

In this short note I will address *the role of a strongly scattering impurities with finite range on the dc conductivity* in a short coherence length superconductor. This is report on the work, done in collaboration with A. Rosengren and B. Altshuler [1].

It is well known that scalar impurities are pair breakers in d -wave and any other nontrivial pairing state superconductor [2–4]. They produce a finite lifetime of the quasiparticles in the nodes of the gap, a finite density of states at low energy, and a *finite* low frequency conductivity at low temperatures, ignoring localization effects. For the special case of a 2D superconductor with a d -wave gap, a straightforward calculation yields the surprising result that dc conductivity $\sigma(\omega \rightarrow 0)$ is a “universal” number [4], *independent* of the lifetime of quasiparticle (but dependent on the anisotropy ratio of the velocities of the quasiparticle in the node of the gap) [5]. However, recent experiments on microwave absorption in YBCO crystals with Zn impurities [6] show a *linear* temperature dependence of the conductivity for pure samples, evolving to the quadratic behavior for higher impurity concentration, and low-temperature conductivity, inversely proportional to the impurity concentration.

i) We find a new *quasi-one-dimensional regime* for dc conductivity in superconductors with a short coherence length ξ , comparable to the range of impurity potential λ . The quasiparticle contribution to dc conductivity is governed by self-energy $\Sigma(\omega \rightarrow 0) = -i\gamma$ and by the phase space available for low-energy quasiparticles. The quasiparticle dispersion is strongly anisotropic in the vicinity of the nodes in a 2D d -wave superconductor: $E_k = \sqrt{v_1^2 k_1^2 + v_F^2 k_3^2}$ and $v_1/v_F \sim \Delta_0/\epsilon_F$. Here we linearized spectrum in the vicinity of the nodal point close to $(\frac{\pi}{2}, \frac{\pi}{2})$, so that k_1 is the momentum along the Fermi surface and k_3 is perpendicular. We find that the overall contribution to the conductivity depends on the ratio of the energy of the quasiparticle to the scattering rate $v_1\lambda^{-1}/\gamma$, λ is the range of the impurity potential, and we get at $T = 0$:

$$\sigma(\omega \rightarrow 0) = \frac{e^2}{2\pi\hbar} \frac{2}{\pi^2} \frac{v_F}{v_1} \left(1 + \left(\frac{\gamma}{2v_1\lambda^{-1}} \right)^2 \right)^{-1/2}. \quad (1)$$

For $v_1\lambda^{-1}/\gamma \ll 1$ quasiparticle dynamics is essentially *quasi-one-dimensional* and conductivity *depends* on the impurity concentration $\sigma_{Q1D} \sim n_{imp}^{-1}$. Our model predicts that the dc

conductivity at low temperature should be *proportional to the scattering rate in the normal state*. This limit might occur in high- T_c superconductors, for which we estimate $\lambda/a \sim 1-3$ and $\Delta_0/\epsilon_F \sim 10^{-1}$. In the limit $\lambda \rightarrow 0$ Eq. (1) gives the “universal” dc conductivity $\sigma_{2D} \sim v_F/v_1$, found in [4].

To explain this effective *change of dimensionality* we note that transverse momentum is limited by $k_1 < 2/\lambda$ and quasiparticle dispersion on such a small scale is irrelevant, compared to γ . The condition for this to occur is precisely $v_1\lambda^{-1}/\gamma \ll 1$. The transverse (along the Fermi surface) scattering does not contribute effectively to the conductivity; we call this case a *quasi-one-dimensional* limit. The existence of this limit is the result of the *finite* impurity range λ [7]. In the opposite limit $v_1\lambda^{-1}/\gamma \gg 1$, which holds for “zero” impurity range, we recover standard unitary scattering results [8–10].

ii) Here we will explain the assumptions we made to calculate conductivity. We assume that impurities are strong scatterers with s-wave phase shift $\delta_0(\mathbf{q}) \simeq \pi/2$, for $|\mathbf{q}| < \lambda^{-1}$, where $\mathbf{q}$ is wavevector, counted from the Fermi wavevector. This assumption is well supported by experiments on cuprates with Zn impurities. The origin of strong potential impurity scattering in high- T_c superconductors is the highly correlated antiferromagnetic nature of the normal state. The second assumption is about the finite range λ of the impurity potential, which plays role of the momentum cut off in the momentum dependence of phase shift $\delta_0(\mathbf{q})$. It is as well motivated by the fact that high- T_c superconductors have a substantial antiferromagnetic coherence length $\xi_{AFM} \sim 3a$ at the transition temperature. A scalar impurity will produce distortions in magnetic correlations on the range of the ξ_{AFM} . On the other hand superconducting coherence length $\xi \sim 20 \text{ \AA}$ is comparable to this scale and thus, the range of the potential is finite on the scale relevant for superconductivity. This point should be contrasted to the case of heavy-fermion superconductors, where the coherence length is $\sim 10^3 \text{ \AA}$, and therefore, any potential impurity will have its range substantially shorter than the coherence length. We retain this cut off finite and on the order of few lattice constants ($\lambda \sim 2a$). This implies that impurities still are well screened and s-wave scattering is dominant.

iii) To calculate the quasiparticle conductivity we use lowest order bubble diagram with self-consistent Green functions with *no vertex corrections*, see for example [4]. For the dc conductivity we get [11]:

$$\sigma(\omega \rightarrow 0) = \frac{e^2}{\hbar} \frac{4v_F^2}{\pi^2} \sum_{\mathbf{k}}' \int d\epsilon (-\partial_\epsilon n(\epsilon)) (|G''(\mathbf{k}, \epsilon)|^2 + |F''(\mathbf{k}, \epsilon)|^2), \quad (2)$$

where, linearizing quasiparticle spectrum in the vicinity of nodes, $G''(\mathbf{k}, \omega = 0) = \gamma/(\gamma^2 + (v_1 k_1)^2 + (v_F k_3)^2)$, $F''(\mathbf{k}, \omega = 0) = 0$. The momentum integral in Eq. (2) is cut off at $|\mathbf{k}| \leq 2/\lambda$ and it yields the final formula Eq. (1) for $T = 0$ with $O(T^2)$ corrections.

For the particular case of strong disorder $v_1 \lambda^{-1}/\gamma \ll 1$, considered in [1], relation between scattering rate in the superconducting state $\gamma = i\Sigma(\omega \rightarrow 0)$ and scattering rate in the normal state $\Gamma = n_{imp}/\pi N_0$ is $\gamma = \pi/8 p_F \lambda \Gamma$. Note that the scattering rate at low temperatures is *linearly* proportional to Γ , as opposed to the $\Gamma^{1/2}$ dependence in the standart unitary scattering case for $v_1 \lambda^{-1}/\gamma \gg 1$. The assumption $v_1 \lambda^{-1}/\gamma \ll 1$ is consistent at $\lambda \sim 2a$ for $\Gamma \geq 20K$. This estimate shows that the *quasi-one-dimensional* regime of quasiparticle scattering should occur in not too clean samples at $T < \gamma$. In this limit scattering rate in the superconducting state is of the same order as the normal state scattering rate $\gamma \sim 2\Gamma \sim 40K$ for $p_F \lambda \sim 6$ and is similar to the scattering rate in the *2D* limit: $\gamma/\tilde{\gamma} \sim \sqrt{\Gamma/\Delta_0} p_F \lambda \simeq 1$. The finite density of states $N(\omega \rightarrow 0)/N_0 = \Gamma/\Delta_0 \sim n_{imp}$, *linear* in impurity concentration, is generated as well.

Using the above estimates we find the conductivity in *quasi-one-dimensional* regime

$$\sigma(\omega \rightarrow 0) = \frac{e^2}{\pi \hbar} \frac{16}{\pi^3} \frac{\hbar}{m \lambda^2 \Gamma}. \quad (3)$$

It is smaller than the normal state conductivity $\sigma(\omega \rightarrow 0)_{\text{normal}} = (e^2/\pi \hbar) (\epsilon_F/\Gamma)$ due to small factor $\hbar/(m \lambda^2 \epsilon_F) \lesssim 1$ with $\lambda > a$. Conductivity is also impurity-dependent, $\sigma_{Q1D} \sim \Gamma^{-1} \sim n_{imp}^{-1}$. This model predicts that the dc σ at low temperatures should be *inversly proportional to the scattering rate in the normal state and to the impurity concentration*. We emphasize that *both* a higher value of the conductivity in the superconducting state *as well as* strong impurity dependence at low temperatures are observed experimentally in

microwave absorption of YBCO [6]. It should be pointed out that we are interested in only elastic scattering and strong inelastic contribution to the scattering rate above T_c is not considered in this model.

iv) One can be almost certain that for dirty enough superconductors the *quasi-one-dimensional* regime will occur, since impurities will lead eventually to a very high scattering rate. The question remains about the competing phenomena, such as the localization of quasiparticles, which might occur earlier than *quasi-one-dimensional* regime. It is interesting to apply this model to the Zn impurities in the YBCO. The applicability of the results presented here to the different high- T_c materials depends on the ratio of scattering rate to the relevant quasiparticle energy. For the same impurity concentration different cuprates may be in different regimes, depending on ξ_{AFM} , Δ_0/ϵ_F , and Γ .

Acknowledgements I would like to thank A. Rosengren and B. Altshuler for collaboration and discussions. I am grateful to E. Abrahams, P. Lee, P. Littlewood, D. Pines and D. J. Scalapino for discussions.

REFERENCES

[†] Also at the Landau Institute for Theoretical Physics, Moscow, Russia.

- [1] A.V. Balatsky, A. Rosengren and B.L. Altshuler, preprint, 1993.
- [2] K. Ueda and T. M. Rice, *Theory of Heavy Fermions and Valence Fluctuations*, Ed. T. Kasuya and T. Saso, (Springer, Berlin, 1985), p. 267.
- [3] L. P. Gor'kov and P. A. Kalugin, Pisma ZhETP, **41**, 208, (1985); JETP Lett., **41**, 253 (1985).
- [4] P. Lee, Phys. Rev. Lett. **71**, 1887, (1993).
- [5] For the semiconductor with Dirac quasiparticle spectrum this result was obtained previously: E. Fradkin, Phys. Rev. **B 33**, 3263 (1986).
- [6] D. Bonn *et al.*, preprint, 1993.
- [7] The fact that impurity scattering is *unitary* is crucial for this *quasi-one-dimensional* limit to occur. Indeed the simple estimate shows that for the *Born* limit with weak scattering $v_1\lambda^{-1}/\gamma \gg 1$.
- [8] P. J. Hirschfeld, P. Wölfle and D. Einzel, Phys. Rev. **B 37**, 83 (1988).
- [9] P. J. Hirschfeld, W. O. Putikka and D. J. Scalapino, preprint, 1993; unpublished.
- [10] P. J. Hirschfeld and N. Goldenfeld, Phys. Rev. **B 48**, 4219 (1993).
- [11] G. Mahan, *Many Particle Physics*, (Plenum, New York, 1990), p. 614.